



# PC PRO BROWN INFIELD TOPDRESSING

## Product Specifications

### Product Data

**Product:**

Pro's Choice Pro Brown Infield Topdressing

**Manufacturer:**

Oil-Dri Corporation of America  
914 Curie Drive, Alpharetta, GA 30005  
1-800-648-1166

**Processing/Shipping Location:**

Ripley, MS 38663

**Description:**

Natural mineral with a blend of Montmorillinite, illite, and amorphous silica. 40% minimum & 60% minimum amorphous silica. Material must be processed via rotary kiln operation at temperatures above 1200° Fahrenheit. Material must be screened and de-dusted.

**Installation:**

The following formula will be a guide for installing PC Pro Brown Topdressing onto your infield. Empty 40-120 bags evenly on skinned area of infield and spread evenly with rake or nail drag. Level and fine drag for even finished appearance. Lightly water for deep red color. Topdress as needed throughout season.

**Mineral Classification:**

Fuller's Earth, Montmorillinite  
(Calcium-Bentonite)

**Color/Appearance:**

Brown

### Technical Data

Product Specifications:	Typical Analysis	Test Procedure
Foreign material	None	SE307.01.01
Bulk density, lbs/ft <sup>3</sup>	44.9 lb/ft <sup>3</sup>	DN001.01.01
pH	6.2	IN001.01.01
Free moisture %	23.7%	VL003.03.02
Hardness %	91.2%	HD001.02.01
Wet Slaking %	15.6%	HD005.01.01
Dust index	.04	PS005.02.02
Grind Distribution	-6 / +16	PS001.02.01
Sieve analysis %		
+6 mesh	0%	
-6/+8 mesh	12%	
-8/+16 mesh	87%	
-16 mesh	2%	

**Item Number:**

A45504G40: 50 lb bags, 40 bags / pallet

